



Perma-Patch

6123 Oakleaf Ave, Baltimore MD 21215
(800) 847-5744 | permapatch.com

PRODUCT INFORMATION

Gator-Aid®

Gator-Aid®

Mastic Filler for Alligatored Paving

USER friendly, complies with all V.O.C. emissions and E.P.A. standards.



GENERAL: Gator-Aid® is a blend of an asphaltic emulsion, mineral fillers, recycled shingles, ground rubber and plasticizers designed especially for alligatored and raveled areas. It is also used for filling cracks in excess of 1" in width on any asphaltic surface. Economically, Gator-Aid® has superior advantages over hot mix skin patch asphalt that requires digging out the alligatored areas and replacing them. It is ready to use on asphaltic surfaces such as athletic courts, driveways, roadways, highways, streets, parking lots, playgrounds, walkways, and running tracks.

SURFACE

PREPARATION: Surface must be dry and free from all loose material, dirt and dust.

APPLICATION: Mix well before using. Use as is. Pour on alligatored areas and work in with flat blade squeegee. Gator-Aid® should be applied no thicker than ¼". Additional applications may be required in severe circumstances.

For Filling Cracks: Fill cracks. Before it sets up, scrape excess from surface (use V-shape rubber squeegee).

For Filling Bird Baths: Should be filled with lifts of ¼" in depth maximum and allowed to harden before any type of seal coating application.

Gator-Aid® will set under good conditions in several hours, depending on weather and filler thickness.

COVERAGE: Up to 20 ft.² for patching alligatored areas and bird baths in ¼" depth. Up to 80 linear feet of ½" X ½" depth cracks.

CAUTION: **KEEP FROM FREEZING.** Do not use when rain is forecast, when surface is wet or when temperature is below 50°F. Wash tools in water. Use a paint thinner if material has dried. Do not store in direct sunlight or where temperatures exceed 100°F. Container should be closed when not in use. Keep out of the reach of children.

PACKAGING: 5 gallon pails.

Material Specifications:

Requirements:

Weight per Gallon @ 77°F, ASTM D1010, (lbs)	10.40 – 10.80
Nonvolatile %, ASTM D2939	67.00 - 70.00
Viscosity @ 77°F, ASTM D562 (Kreb's Stormer Unit)	125 min.
Penetration (0.1 mm), ASTM D5	< 50
Resistance to water, ASTM D2939	no blistering, no re-emulsification
Flammability	non flammable

This information is to assist customers in determining if this product is suitable for the proposed application, and to satisfy themselves as to the suitability of the contents. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent implied. Published technical data and instructions are subject to change without notice. Contact your Allstates Coatings representative for additional technical data and instruction.